


- product name : EPRON VEN

Product is compliant with directive 2004/42/EC



building sector
see note 1
2004/42
IIAi(500)480

pictogram legend

2004/42 Reference to EC Directive
IIBe Annex, Table and Sub-category of product
(840) Limit value of VOC with reference to the product sub-category
550 Maximum VOC content in product ready for use

термостойкость: 90 °C

срок годности: 24 months at + 5/35 °C

note 1: 0% thinning - catalyse with QA 2028
10% thinning - catalyse with QA 2066

- рекомендуемые циклы

1-продуктовый цикл по черным конструкциям в антикоррозионной защите

1 pre-treatment	: sandblasting grade SA 2^{1/2} - 3
2 one coat of	: EPRON EN (80-100 µm)
3 one coat of	: EPRON EN (80-100 µm)

2 2-х продуктовый цикл по черным конструкциям в антикоррозионной защите

1 pre-treatment	: sandblasting grade SA 2 1/2 - 3
2 one coat of	: EPRON EN (80-100 µm)
3 one coat of	: ISOPOL Z (40/50 µm)

3 1-продуктовый цикл на оцинкованных поверхностях

1 pre-treatment	: легкая шлифовка или травление подходящие агрессивные растворы
2 one coat of	: EPRON EN (50-70 µm) 75-85 gloss

проведенные испытания:

Цикл 1: Соответствует ISO 12944 C-4 M.
Испытание проведено во внешней лаборатории в
июле 2017 г.